



## Jewellery Clay

v11076

Especially fine, soft, oven-hardening jewellery clay - can be rolled very thin while maintaining extreme detail and patterns - bake clay in a household oven at 110°C for 30 minutes per 6mm of thickness

### *Comment faire*



**1** Roll 3 coloured balls and place them on top of each other - press the clay lightly together.



**2** Roll the clay to the required thickness using a rolling pin - you could use the removable discs to the rolling pin.



**3** Press a shape cutter through the clay to cut out the shape.



**4** Gently make a hole using a needle.



**5** When the clay is baked in the oven and cooled, apply FIMO Clay Varnish with a soft brush.